



# ARASH MAHYA PARAFFIN MANUFACTURING CO.

## SEMI-REFINED PARAFFIN WAX

### PRODUCT DATA SHEET

CHARACTERISTIC	RESULT	METHOD
Oil Content	4-6 %wt	ASTM D-721
Melting Point	62 – 65 °C	ASTM D-87
Flash Point	220-240 °C	ASTM D-92
Kinematic Viscosity at 100 °C	6-7.5 CST	ASTM D-445
Colour (Lovibond)	Yellowish white	Method (2"cell)

#### Packing:

Carton / PP Bags / Metalized Bags

#### Application:

Candles, Match sticks, Tires, cosmetics, wooden boards, tarpaulin, etc.

#### Head Office:

No 48, 9<sup>th</sup> Flr, Mina Tower,  
Sadeqieh Square,  
Tehran, Iran.

#### Tel:

+98 21 440 710 24  
+98 21 440 710 26  
+98 21 440 710 28

#### Email:

info@arashmahya.com  
arashmahyaco@gmail.com

**Website:** [www.arashmahya.com](http://www.arashmahya.com)